




# CUPA 2


---

*Non-carbonated slate formed by tectonic compression.  
Dark grey slate with thin laminations and a smooth surface.*



 Valdacal mine, Carballeda de Valdeorras (Ourense) Spain.

 Operating since 1972.

 Sizes: 20x20 - 60x45 cm  
Thickness: 3.5 - 5 - 6 - 7.5 mm



## Formats



Rectangular Square Half Moon Waben Schuppen Fishschuppen 90° Sawn

## Selections



## Technical specifications

ABSORPTION	CARBONATE NON CARBONATED	MOR CHARACTERISTIC	SO <sub>2</sub> EXPOSURE TEST	THERMAL CYCLE TEST	FREEZE THAW TEST
0,18% Code: W1 (< 0,4%)	0,28% Complies (< 1,5%)	Longitudinal 49,6 MPA Transverse 39,4 MPA	S1	T1	Fullfil < 0,6%

## International certifications



European Standard: EN 12326 | French Specifications: NF 02/12 N° 35138 | Belgian Specifications: ATG H930